

IUPITAL® ACETAL COPOLYMER

ENGINEERING THERMOPLASTIC

IUPITAL® IS A REGISTERED TRADEMARK OF MITSUBISHI ENGINEERING PLASTICS CORPORATION

IUPITAL® F20

IUPITAL® F20-01 / F20-02 / F20-03 are the standard medium viscosity (medium melt flow) grades in the Iupital® Polyacetal range and are suited to general purpose injection moulding applications. Offering an exceptional combination of processability, rigidity, frictional wear, heat and chemical resistance, typical applications include mechanical clips, lock linkages and automotive petrol caps.

Note: [No mould release = 01] / [Standard mould release = 02] / [Low mould deposit = 03].

Note: The letters "UV" or "W" indicate UV stabilisation has been added [ie: Iupital® F20-03-W].

	<u>CONDITIONS</u>	<u>UNITS</u>	<u>TYPICAL VALUES</u>	<u>TESTING METHODS</u>
<u>1. Mechanical Properties</u>				
Notched Izod Impact Strength	12.7 x 3.2 mm	J/m	64	ASTM D256
Tensile Strength	12.7 x 3.2 mm @ 20 mm/min	MPa	61.3	ASTM D638
Elongation to Fail	12.7 x 3.2 mm @ 20 mm/min	%	60	ASTM D638
Flexural Strength	12.7 x 6.4 mm @ 2.8 mm/min	MPa	89.7	ASTM D790
Flexural Modulus	12.7 x 6.4 mm @ 2.8 mm/min	MPa	2600	ASTM D790
Shear Strength	2.0 mm	MPa	54.9	ASTM D732
Tensile Impact Strength	1.6 mm	kJ/m ²	120	ASTM D1822
<u>2. Thermal Properties</u>				
Heat Deflection Temperature	12.7 x 6.4 mm @ 1.82 MPa	°C	110	ASTM D648
	12.7 x 6.4 mm @ 0.46 MPa	°C	158	ASTM D648
Melting Temperature		°C	165	DSC
Coefficient of Linear Thermal Expansion		cm/cm/°C	13 exp-5	ASTM D696
<u>4. Physical Properties</u>				
Melt Flow Rate	190°C, 2.16 kg	g/10 min	9.0	ASTM D1238
Specific Gravity		-	1.41	ASTM D792
Rockwell Hardness		M	80	ASTM D785
UL Flammability	0.8 mm	Rating	HB	UL 94
Water Absorption	24 hours	%	0.22	ASTM D570
Mould Shrinkage	3.0 x Ø100 mm disc	%	2.0±0.4	ASTM D955
<u>5. Electrical Properties</u>				
Volume Resistivity	-	Ohm.cm	1.0 exp +14 -	

All test results were obtained using natural material.

Issued: November 2000

Material Safety Data Sheet (MSDS): Code AC

Marplex Australia Pty. Ltd. makes no representation with regard to the completeness or accuracy of the information and any recommendations contained in this data sheet, and accepts no responsibility for loss or damage whatsoever resulting from the use of, or reliance upon, the information and any recommendation herein. Marplex Australia Pty. Ltd. products are sold on standard terms and conditions, a copy of which is available on request.

MARPLEX AUSTRALIA PTY. LTD. 221 BROWNS ROAD, NOBLE PARK, VICTORIA 3174

CUSTOMER SERVICE: PHONE 03 8710 1415, 1800 627 987, FAX 03 9795 6300

TECHNOLOGY DEPARTMENT: PHONE 03 8710 1432, FAX 03 9795 1800

SALES OFFICES: MELBOURNE 03 8710 1400 • SYDNEY 02 9891 0044 • ADELAIDE 08 8274 3710
BRISBANE 07 3842 3152 • PERTH 08 9429 8814 • AUCKLAND, NZ 09 633 0233

TYPICAL PROCESSING CONDITIONS

IUPITAL® F20

The following typical guidelines are offered as initial processing conditions for IUPITAL® F20. In practice, processing parameters may need to be varied to give commercially acceptable performance in conjunction with optimum physical properties. For specific technical advice on part design or processing conditions, contact the Marplex Technical Service Department.

Temperature of pellet bed in dehumidifying drier	80 - 90 °C
Minimum drying time at desired pellet bed temp	2 - 3 hours
Mould temperature	50 - 90 °C
Nozzle temperature	Do not exceed stock temperature
Stock temperature	190 - 210 °C
Cylinder temperatures	Rear 165 - 185 °C
	Middle 175 - 195 °C
	Front 185 - 205 °C
Fill speed	Medium - Fast
Screw speed	40 - 60 rpm
Screw back pressure	0.1 - 0.5 MPa
Injection pressure	60 - 130 MPa
Clamp pressure	3 - 5 kN/cm ²

Comment(s):

- 1 Cleanliness of the dryer, machine hopper and machine screw/barrel/nozzle assembly are essential for processing Iupital® Polyacetal and producing contamination free moulded components.
- 2 Iupital® Polyacetal is not compatible during moulding with other polymers.
- 3 It is suggested that the pre-drying, moulding die and material temperatures are manually confirmed using a hand held temperature measuring device.

Conversions: 1 MPa = 145 psi
= 10.2 kg/cm²
= 10 bar
°C = 5(°F-32)/9
1 kN/cm² = 0.65 ton/in²